



CERVINO (Flat Woven)



 EN 14041: 2004	
Specification and tolerances in according EN 1307	

Costruzione	Technique de fabrication	Construction	Herstellungsverfahren
Tessuto-Riccio	Tissée-Bouclé	Woven-Loop pile	Gewebt-Schlinge
Composizione 100% poliammide 6 SD	Composition du velours 100% polyamide 6 SD	Pile composition 100% polyamid 6 SD	Polnutzschicht 100% polyamid 6 SD
Sottofondo Juta sintetica	Dossier Jute synthétique	Secondary backing Synthetic jute	Rückenausrüstung SDR Textilrucken
Punti al m² ± 164000	Touffes au m² ± 164000	Stitches per m² ± 164000	Knoten m² ± 164000
Altezza pelo ± 2.0 mm	Hauteur du velours ± 2.0 mm	Pile height ± 2.0 mm	Polhöhe ± 2.0 mm
Altezza totale ± 3.0 mm	Hauteur totale ± 3.0 mm	Total height ± 3.0 mm	Gesamtdicke ± 3.0 mm
Peso della fibra ± 400 g/m ²	Poids du velours ± 400 g/m ²	Yarn weight ± 400 g/m ²	Polgewicht ± 400 g/m ²
Peso totale ± 1750 g/m ²	Poids total ± 1750 g/m ²	Total weight ± 1750 g/m ²	Gesamtgewicht ± 1750 g/m ²
Larghezza rotolo 400 cm	Largeur du rouleau 400 cm	Roll width 400 cm	Breite 400 cm



Colour fastness to light	≥ 5	Thermal resistance m ² K/W	0,06
Insulation impact noise ΔL _w	16 dB	Body voltage walking test kV	≤ 2
Acoustical absorption α _w	0,15	Treatment	Soil Protection

RESISTENZA – WEARABILITY RESISTANCE - STRAPAZIERWERT				COMFORT – COMFORT CONFORT - KOMFORTWERT			
estrema extreme extrême extrem	elevata high élevée stark	normale good normale normal	sufficiente normal suffisante gering	medio medium moyen einfach	buono good bon gut	alto very good élevé hoch	ottimo excellent excellent luxuriös

Approved by Technique Management: M. Medica

Date: 05/03/2020

Radici Pietro I&B. reserves the right to modify the characteristics of the product while keeping the same technical properties.